

PRESSPAPER
Classe A – 105°C

Nº	Properties	Unit	Values			
1	Thickness	mm	0.1	0.15-025	0.30-0.35	0.40-0.50
2	Thickness Tolerance ≤	%	±10			
3	Density	g/cm ³	1.0-1.2			
4	Tensile Strength ≥	MD	80			
		CD	40			
5	Dielectric Strength ≥	In Air No Bending	9	10	10	9
		In Air After Bending	7	8	8	7
		In Oil	---			
6	Shrinkage ≤	MD	---			
		CD	---			
7	Elongation ≥	MD	---			
		CD	---			
8	Conductivity of aqueous extract ≤	Ms/m	8.0			
9	PH Value of Aqueous Extract	---	6.0-9.0			
10	Ash Content ≤	%	1			
11	Moisture Content ≤	%	8			
12	Availability	---	Form: roll Colour: natural brown			

CÓPIA NÃO CONTROLADA – SUJEITO A ALTERAÇÃO